



727 South 950 West • Woods Cross, Utah 84087
Phone (801) 298-4581

V-418**PRODUCT DATA****RED OXIDE PRIMER**

PRODUCT DESCRIPTION: V-418 TT-P-664 FEDERAL SPECIFICATION RED OXIDE PRIMER COATING, ALKYD, CORROSION-INHIBITING, LEAD AND CHROMIUM FREE, VOC COMPLIANT. Excellent for fast handling of steel. After proper cure time this primer is suitable for use under a wide range of high performance topcoats, including epoxies, urethanes, and acrylic enamels.

INTENDED USES: Shop coating or field priming weather-exposed structural and miscellaneous steel tanks, machinery, and equipment to be top coated with most oil, alkyd, or latex topcoats. Do not use on galvanized metal or immersion service. For optimum performance a topcoat is required for exterior exposures.

SURFACE PREPARATIONS: For best results, it is important that all surface contaminants, such as moisture, oil, dirt, rust, and mill scale be removed before application of this primer. Can be applied to either blasted, hand, or power tool cleaned steel. A minimum of SSPC-2 hand tool cleaning required.

PHYSICAL INFORMATION

COLOR: RED OXIDE

GLOSS LEVEL: FLAT

SOLIDS BY WEIGHT: 72%

RECOMMENDED DRY FILM THICKNESS: 1.5-2.5 MILS

THEORETICAL COVERAGE: 350-400 SQ FT PER GALLON

METHOD OF APPLICATION: AIRLESS SPRAY, AIR SPRAY, BRUSH, AND ROLLER

DRYING TIME – AT 75 F

TO TOUCH: 15-20 MINUTES

TO HANDLE: 30-90 MINUTES

TO RECOAT: 4-12 HOURS

REGULATORY DATA

FLASHPOINT: 80 F

PRODUCT WEIGHT: 11.86 LB

VOC: 3.36 Pounds per Gallon



727 South 950 West • Woods Cross, Utah 84087
Phone (801) 298-4581

PRODUCT DATA

RED OXIDE PRIMER

APPLICATION

MIXING: This material is a one-component coating and should always be mixed thoroughly with a power agitator before application.

MIX RATIO: Not applicable

WORKING POT LIFE: Not applicable

AIRLESS SPRAY: Recommended Tip range 15-17 thou (0.38-0.43 mm)
Total output fluid pressure at spray tip not less than 2,500 p.s.i.

AIR SPRAY: Recommended Gun DeVilbiss MBC or JGA
(Pressure Pot) Air Cap 704
Tip E

BRUSH: Suitable Typically 1.5-2.0 mils can be achieved. Care should be taken to avoid under application.

ROLLER: Suitable Typically 1.5-2.0 mils can be achieved. Care should be taken to avoid under application.

THINNER: Xylene Do not thin more than allowed by local environmental legislation.

CLEANER: Xylene

WORK STOPPAGES: Thoroughly flush all equipment with xylene. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and / or viscosity increase of the material after storage. Material should be filtered prior to use.

CLEAN UP: Clean all equipment immediately with xylene. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.

All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations / legislation.

SYSTEM COMPATIBILITY

The following topcoats are recommended for V-418 red oxide primer.

- Alkyds
- Silicone Alkyds
- Latex
- Acrylic Enamels
- Urethanes
- Epoxies

SHIPPING & STORAGE

NUMBER OF COMPONENTS: 1

PACKAGED IN: 55-Gallon Drums, 5 Gallon Pails, and 1 Gallon Cans

STORAGE TEMPERATURE: Minimum 20 F. Maximum 110 F.

Information provided herein is based upon tests believed to be reliable. Inasmuch as Valley Paint, Inc. has no control over the exact manner in which others may use this information, it does not guarantee the results to be obtained. Nor does the Company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.